



PETRO AZAR ASIA



BITUMEN 60/70

ANALYSIS	UNIT	LIMIT	TEST METHOD
Density @ 25°C(max)	Kg/L	1.01-1.06	ASTM D71 or D3289
Penetration @ 25°C	mm/10	60-70	ASTM D5
Softening Point	°C	49-56	ASTM D36
Ductility @ 25°C (min)	cms	100	ASTM D113
Loss on heating (max)	Wt.%	0.2	ASTM D6
Drop in penetration After Heating (max)	%	20	ASTM D5-D6
Flash point (min)	°C	232	ASTM D92
Solubility in CS ₂ (min)	Wt.%	99.5	ASTM D4
Spot Test	-	Negative	A.A.S.H.O.T102